


Mirafi[®] BXG12



Mirafi[®] BXG12 geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns which are woven in tension and finished with a PVC coating. Mirafi[®] BXG12 geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas Laboratories are accredited by a2La (The American Association for Laboratory Accreditation) and Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CMD
Tensile Strength (at ultimate)	ASTM D6637	lbs/ft (kN/m)	2500 (36.5)	4500 (65.7)
Tensile Strength (at 1% strain)	ASTM D6637	lbs/ft (kN/m)	375 (5.5)	530 (7.7)
Tensile Strength (at 2% strain)	ASTM D6637	lbs/ft (kN/m)	625 (9.1)	840 (12.3)
Tensile Strength (at 5% strain)	ASTM D6637	lbs/ft (kN/m)	1000 (14.6)	1350 (19.7)
Tensile Modulus (at 1% strain)	ASTM D6637	lbs/ft (kN/m)	37500 (547)	53000 (773)
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70	

Physical Properties	Unit	Typical Value
Percent Open Area (COE CW-02215)	%	70
Grid Aperture Size (MD)	in (mm)	1.0 (25.4)
Grid Aperture Size (CMD)	in (mm)	1.0 (25.4)
Mass/Unit Area (ASTM D5261)	oz/yd ² (g/m ²)	11.4 (386)
Roll Dimensions (width x length)	ft (m)	13.1 x 164 (4 x 50)
Roll Area	yd ² (m ²)	239 (200)
Estimated Roll Weight	lbs (kg)	200 (91)

© 2013 TenCate Geosynthetics Americas
Mirafi[®] is a registered trademark of Nicolon Corporation

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

UV Resistance (ASTM D4355), Percent Open Area (COE CW-02215), and Grid Aperture Size is not covered by our current A2LA accreditation



Fax 706 693 4400
www.tencate.com



GAI-LAP-25-97



Testing Lab 1291.01 & 1291.02